

## **General Information**

**TAFMER<sup>™</sup> PN-2070**, propylene based polymer, is a specialty olefinic resin designed to improve transparency, flexibility, softness and impact resistance of Polypropylene (PP).

| Physical Attributes:         | Low specific gravity<br>High melting point<br>Softness and elasticity<br>Excellent transparency due to nano-size controlled crystals<br>Good impact resistance<br>Anti-stress whitening |
|------------------------------|---|
| Chemical Attributes:         | PP miscibility  |
| FDA/EU Directive Conformity: | Conforms to FDA and EU Directive<br>Please contact Mitsui sales representatives for more information  |
| Others:                      | Packed in pellet form<br>Gel content controlled   |

| Physical Properties        | Test Method                   | UNIT    | Value  |
|----------------------------|-------------------------------|---------|--------|
| MFR(230°C)                 | ASTM D1238                    | g/10min | 7.0    |
| Transmittance              | MCI Method<br>in Cyclohexanol | %       | 98     |
| Mechanical Properties      | Test Method                   | Unit    | Value  |
| Yielding Strength          | ASTM D638                     | MPa     | -      |
| Tensile Strength at Break  | ASTM D638                     | MPa     | > 14   |
| Elongation at Break        | ASTM D638                     | %       | > 1000 |
| Young's Modulus            | ASTM D638                     | MPa     | 14     |
| Surface Hardness (Shore A) | ASTM D2240                    | -       | 75     |
| Thermal Properties         | Test Method                   | Unit    | Value  |
| Melting Point              | MCI Method                    | °C      | 140    |
| Brittleness Temperature    | ASTM D746                     | °C      | -28    |

## **Disclaimer:**

Information contained herein is based on the material, information and data available as of the end of December 2011. No warranty is given for any data or evaluation results contained herein. It is also assumed that the product is to be used under normal conditions and with due precautions. If the product is to be used in any special manner, the user is requested safety measures to meet such new use or application.

