

TAFMER XM Technical Data Sheet

Item			XM-7070	XM-7080
Melting Point	DSC	°C	75	83
MFR 230°C	ASTM D 1238	g/10min	7	7
Yield Stress	ASTM D 638	MPa	11	13
Tensile Strength		MPa	34	36
Elongation		%	>600	>600
Young's Modulus		MPa	290	390
Surface Hardness	ASTM D 2240	Shore-D	52	55
Vicat Softening Point	ASTM D 1525	°C	67	74