

# Desmopan 89785A

/ Grade for calendering; no yellowing under the action of UV light; very good low-temperature impact strength; high rebound resilience; improved microbial resistance; Improved hydrolysis resistance; Textile coating

| 性能            | 测试条件         | 单位    | 标准                      | 数值                          |          |       |
|---------------|--------------|-------|-------------------------|-----------------------------|----------|-------|
|               |              |       |                         | drying                      | annealed | -     |
|               |              |       |                         | according to specifications |          |       |
| 机械性能          |              |       |                         |                             |          |       |
| C 邵氏硬度 A      | 1s           | -     | DIN ISO 7619-1          |                             | 86       |       |
| C 压缩率         | 24 h; 70 ° C | %     | DIN ISO 815-1, Method A |                             | 40       |       |
| C 压缩率         | 72 h; 23 ° C | %     | DIN ISO 815-1           |                             | 20       |       |
| C 耐磨性         |              | mm³   | ISO 4649 method A       |                             | 30       |       |
| C 回弹力         |              | %     | ISO 4662                |                             | 65       |       |
| C 撕裂强度        | 500 mm/min   | kN/m  | ISO 34-1                |                             | 75       |       |
| 其他性能 (23 ° C) |              |       |                         |                             |          |       |
| C 密度          |              | kg/m³ | ISO 1183-1              |                             |          | 1080  |
| 注塑条件          |              |       |                         |                             |          |       |
| C 注塑-熔体温度     |              | °C    | —                       | 200-220                     |          |       |
| C 注塑-模具温度     |              | °C    | —                       |                             |          | 20-40 |
| C 挤出-熔体温度     |              | °C    | —                       | 190                         |          |       |

C 这些性能数据来源于 CAMPUS 塑料数据库并且依据 ISO 10350 标准的国际分类原则

# Desmopan 89785A

## 声明

---

Covestro AG  
Business Unit Polyurethanes  
Kaiser-Wilhelm-Allee 60  
51373 Leverkusen  
Germany  
[www.TPU.covestro.com](http://www.TPU.covestro.com)  
[www.covestro.com](http://www.covestro.com)