

Desmopan 6580A MVT GMP

/ Extrusion grade; very good hydrolysis and microbial resistance; high moisture vapor transmission rate; This product is manufactured under Good Manufacturing Practice (GMP defined in Regulation (EC) No. 2023/2006) and is therefore limited suitability for use with food contact. Please refer our separate certificate at <http://www.tpu.covestro.com/en/Library/Certificates/Food-Contact.aspx>; Application; breathable films; Textile coating

性能	测试条件	单位	标准	数值
				drying annealed - according to specifications
机械性能				
C 邵氏硬度 A	1s	-	DIN ISO 7619-1	79
C 最终拉伸强度	200 mm/min	MPa	DIN 53504	34
C 断裂应变	200 mm/min	%	DIN 53504	920
C 100% 应变时的应力	200 mm/min	MPa	DIN 53504	4
C 300% 应变时的应力	200 mm/min	MPa	DIN 53504	17, 6
注塑条件				
C Drying Temperature		°C	-	80-110

C 这些性能数据来源于 CAMPUS 塑料数据库并且依据 ISO 10350 标准的国际分类原则



Desmopan 6580A MVT GMP

声明

Covestro AG
Business Unit Polyurethanes
Kaiser-Wilhelm-Allee 60
51373 Leverkusen
Germany
www.TPU.covestro.com
www.covestro.com