

# K-Resin BK10

Styrene Butadiene Copolymer (SBC)

## TECHNICAL DATASHEET

### DESCRIPTION

K-Resin® BK10 process very well in injection molding, providing good cycle times and design flexibility. Applications range from containers and packaging with living hinges to medical applications, toys, displays, overcaps and hangers. INEOS Styrolution has several grades of K-Resin® SBC tailored for your injection molded needs.

### FEATURES

- Excellent Clarity
- Good Stiffness
- Good Toughness
- High Surface Gloss
- Higher melt flow

### APPLICATIONS

- Molded Containers and Bottles
- Medical Devices
- Overcaps
- Displays
- Toys

Property, Test Condition	Standard	Unit	Values
<b>Rheological Properties</b>			
Melt Volume Rate, 200 °C/5 kg	ISO 1133	cm³/10 min	14
<b>Mechanical Properties</b>			
Charpy Notched Impact Strength, 23° C	ISO 179/1eA	kJ/m²	2
Tensile Stress at Yield, 23 °C	ISO 527	MPa	25
Tensile Strain at Yield, 23 °C	ISO 527	%	2.2
Tensile Strain at Break, 23 °C	ISO 527	%	180
Tensile Modulus	ISO 527	MPa	1500
Flexural Strength, 23 °C	ISO 178	MPa	28
Flexural Modulus, 23 °C	ISO 178	MPa	1400
Hardness, Shore D	ISO 868	-	63
<b>Thermal Properties</b>			
Vicat Softening Temperature VST/B/50 (50N, 50 °C/h)	ISO 306	°C	53
Vicat Softening Temperature, VST/A/50 (10N, 50 °C/h)	ISO 306	°C	84
Heat Deflection Temperature, B (0.45 MPa)	ISO 75	°C	76
Heat Deflection Temperature A; (annealed 4 h/80 °C; 1.8 MPa)	ISO 75	°C	61

# K-Resin BK10

Styrene Butadiene Copolymer (SBC)

## TECHNICAL DATASHEET

Property, Test Condition	Standard	Unit	Values
Coefficient of Linear Thermal Expansion	ISO 11359	10 <sup>-6</sup> /°C	60 - 90
<b>Optical Properties</b>			
Refractive Index, Sodium D Line	ISO 489	-	1.57
Light Transmission at 550 nm	ASTM D 1003	%	92
Haze	ASTM D 1003	%	< 0.9
<b>Other Properties</b>			
Density	ISO 1183	kg/m <sup>3</sup>	1020
Water Absorption, Saturated at 23 °C	ISO 62	%	0.07
<b>Processing</b>			
Linear Mold Shrinkage	ISO 294-4	%	0.3 - 1

The nominal properties herein are typical of the product but do not reflect normal testing variance and therefore should not be used for specification purposes. Values are rounded.

[Tensile Yield Strength/Tensile Elongation @ Break] = Type 1 @ 2 in/min (50 mm/min)

[Flexural Modulus/Flexural Yield Strength] = 0.125 in (3.2 mm) specimen @ 0.5 in/sec (1.27 cm/min)

[Instrumented Impact Total Energy] = 0.125 in (3.2 mm) specimen @ 150 in/sec (381 cm/sec) impact rate

## DISCLAIMER

The aforementioned data shall constitute the agreed contractual quality of the product sold by INEOS Styrolution at the time of passing of risk. INEOS Styrolution does not make any further warranty, representation or guarantee of any kind, express or implied, regarding the suitability of the product for any particular purpose or application and INEOS Styrolution disclaims all liability in connection therewith. The customer himself is required to verify whether or not the product is suitable for the further processing or application intended and whether or not the product complies with the relevant statutory requirements. Unless explicitly and individually otherwise agreed in writing, INEOS Styrolution's sole and exclusive liability with respect to its products is set forth in INEOS Styrolution's General Terms and Conditions for Sale.