

Shanghai SECCO Petrochemical Co., Ltd.

Add: 30F, A Building, Far East International Plaza

No.299, Xian Xia Road, Shanghai 200051 P.R. China

Tel: (021) 52574688-3333 (customer service) Fax: (021) 62783737 (customer service)

Email: customerservice@secco.com.cn Website: http://www.secco.com.cn

10/2011

SECCO GPPS123

General Purpose Polystyrene Resin

Product description

GPPS123 retains high fluidity and good mould release and allows excellent transparency and gloss.

Product characteristics

Typical properties

Properties	Test method	Test condition	Units	Typical values
Melt flow rate	ISO1133	200°C/5kg	g/10min	8
Tensile strength at yield	ISO527-2	50mm/min	MPa	47
Tensile strength at break	ISO527-2	50mm/min	%	2
Tensile elongation at break	ISO178	2mm/min	MPa	3100
Flexural modulus	ISO178	2mm/min	MPa	75
Flexural strength	ISO179	23°C/1eU	kJ/m ²	9
Notched Izod impact strength	ISO306	B50/oil	$^{\circ}$ C	91
Vicat softening temperature	ISO75-2	1.8MPa	$^{\circ}\! \mathbb{C}$	73
Heat distortion temperature	ISO1183		kg/ m ³	1040
Rockwell hardness	ISO13468-1		%	90
Density	ISO62		%	<0.1
Water absorption	UL 94		Class	94HB
UL flammability	ISO294-4		%	0.4-0.6

¹⁾ Values given are typical and should not be interpreted as specification.

Additional information

Application

CD case, cassette, one-way plastic drinking cup, compote, medical vessel, tableware, stationery, beads for decoration, etc.

Product compliance

GPPS123 complies with the national hygienic standard for polystyrene resin used as food packaging, FDA regulation CFR 177.1640(c) (1) and the RoHS Directive 2002/95/EC. *GPPS123* has obtained the UL certificate of the USA. However, the customer is still responsible for determining whether the fabricated product is in compliance with applicable laws and regulations.

Safety and material handling

SECCO polystyrene resin has a very low degree of toxicity under normal conditions of use. Please contact your SECCO representative or the local suppliers for more detailed information and/or Material Safety Data Sheet (MSDS) for the specific grade of interest.

The data contained in this document are based on our typical testing, and relate only to the named product or materials when not in combination with any other product or materials. Customers and other users are responsible for determining whether products and the information in this document are appropriate for their use and for ensuring that disposal practices are in compliance with applicable laws and other governmental enactments. SECCO does not accept any liability whatsoever arising from the use of this information or the use, application or processing of any product described herein.

²⁾ Typical applications of GPPS123 are injection molding and co-extruded gloss top layer-HIPS sheets. It is suggested that the injection temperature should be set at 180°C-240°C, and mould temperature at 30-60°C.