



SHANGHAI SECCO PETROCHEMICAL CO LTD

557 Nan Yinhe Rd
Shanghai Chemical Industry Park
Shanghai, Shanghai Shi 201507 China



HIPS622

Polystyrene (PS), pellets

可燃性	值	测试方法
UL 阻燃等级		
1.5 mm, NC	HB	UL 94
3.0 mm, NC	HB	UL 94
3.0 mm, NC	HB40	IEC 60695-11-10, -20
1.5 mm, NC	HB75	IEC 60695-11-10, -20
电气性能	值	测试方法
热丝引燃 (HWI)		UL 746A
1.5 mm	PLC 4	
3.0 mm	PLC 3	
高电弧燃烧指数(HAI)		UL 746A
1.5 mm	PLC 0	
3.0 mm	PLC 0	
高电压电弧起痕速率 (HVTR)	PLC 1	UL 746A
热性能	值	测试方法
RTI Elec		UL 746B
1.5 mm	50.0 °C	
3.0 mm	50.0 °C	
RTI Imp		UL 746B
1.5 mm	50.0 °C	
3.0 mm	50.0 °C	
RTI		UL 746B
1.5 mm	50.0 °C	
3.0 mm	50.0 °C	