

HOSTAFORM® LX270Z XAP®2

Hostaform® acetal copolymer grade LX270Z XAP®2 is a UV stabilized material available in a range of molded in metallic colors generally for automotive interior applications and is a higher flow grade than LX90Z. In addition, Hostaform® LX270Z XAP®2 has lower volatile emissions as required for some automotive interiors. Flow properties of this grade is based upon the standard acetal acetal copolymer and flow testing does not reflect how it actually flows. Besides material, optimal finish for specialty metallic parts is dependent on proper drying, gate design, knit line locations, and special processing. Please contact Celanese Technical Service for assistance with your application.

Typical mechanical properties

Tensile Modulus	3100	MPa	ISO 527-1/-2
Yield stress, 50mm/min	55	MPa	ISO 527-1/-2
Flexural Modulus	2930	MPa	ISO 178
Charpy notched impact strength, 23°C	3	kJ/m²	ISO 179/1eA

Thermal properties

Melting temperature, 10°C/min	167	°C	ISO 11357-1/-3
Temp. of deflection under load, 1.8 MPa	90	°C	ISO 75-1/-2
Coeff. of linear therm. expansion, parallel	105	E-6/K	ISO 11359-1/-2
Coeff. of linear therm. expansion, normal	94	E-6/K	ISO 11359-1/-2

Other properties

Density 1430 kg/m³ ISO 1183

Other Approvals

Other Approvals

OEM	Specification	Additional Information
Stellantis - Chrysler	CPN 5080	100% Color match

Printed: 2023-08-07 Page: 1 of 1

Revised: 2023-02-23 Source: Celanese Materials Database

NOTICE TO USERS: Values shown are based on testing of laboratory test specimens and represent data that fall within the standard range of properties for natural material. These values alone do not represent a sufficient basis for any part design and are not intended for use in establishing maximum, minimum, or ranges of values for specification purposes. Colourants or other additives may cause significant variations in data values. Properties of moulded parts can be influenced by a wide variety of factors including, but not limited to, material selection, additives, part design processing conditions and environmental exposure. Other than those products expressly identified as medical grade (including by MT® product designation or otherwise), Celanese's products are not intended for use in medical or dental implants. Regardless of any such product designation, any determination of the suitability of a particular material and part design for any use contemplated by the users and the manner of such use is the sole responsibility of the users, who must assure themselves that the material as subsequently processed meets the needs of their particular product or use. To the best of our knowledge, the information contained in this publication is accurate; however, we do not assume any liability whatsoever for the accuracy and completeness of such information. The information contained in this publication should not be construed as a promise or guarantee of specific properties of our products. It is the sole responsibility of the users to investigate whether any existing patents are infringed by the use of the materials mentioned in this publication. Moreover, there is a need to reduce human exposure to many materials to the lowest practical limits in view of possible adverse effects. To the extent that any hazards may have been mentioned in this publication, we neither suggest nor guarantee that such hazards are the only ones that exist. We recommend that persons intending to rely on any recommendation or to use any eq

© 2023 Celanese or its affiliates. All rights reserved. Celanese®, registered C-ball design and all other trademarks identified herein with ®, TM, SM, unless otherwise noted, are trademarks of Celanese or its affiliates. Fortron is a registered trademark of Fortron Industries LLC. KEPITAL is a registered trademark of Korea Engineering Plastics Company, Ltd.