

KEPITAL[®] FG2025

A 25% glass fiber-reinforced grade

KEPITAL® FG2025 is a 25% glass fiber-reinforced grade for general injection molding. Suitable for parts requiring extermely high strength, high stiffness, high deflection temperature, and excellent creep resistance.

Rheological properties

Moulding shrinkage, parallel	0.7	%	ISO 294-4, 2577
Typical mechanical properties			
Tensile Modulus	9000	MPa	ISO 527-1/-2
Stress at break, 5mm/min	160	MPa	ISO 527-1/-2
Strain at break, 5mm/min	3	%	ISO 527-1/-2
Flexural Modulus	8250	MPa	ISO 178
Flexural Strength	220	MPa	ISO 178
Charpy notched impact strength, 23°C		kJ/m²	ISO 179/1eA
Charpy notched impact strength, -30 °C	8	kJ/m²	ISO 179/1eA
Poisson's ratio	0.343		
Thermal properties			
Melting temperature, 10°C/min	165	°C	ISO 11357-1/-3
Electrical properties			
Electric strength	23	kV/mm	IEC 60243-1
Other properties			
Humidity absorption, 2mm	0.2	%	Sim. to ISO 62
Density	1590	kg/m³	ISO 1183
-		-	

Other Approvals

Other Approvals

OEM	Specification	Additional Information
GM	GMW17968P-POM- GF25	Natural & Black
Ford	WSS-M98P14-A3	ASN 9954



KEPITAL[®] FG2025

Printed: 2023-08-07

Revised: 2023-06-27 Source: Celanese Materials Database

Page: 2 of 2

NOTICE TO USERS: Values shown are based on testing of laboratory test specimens and represent data that fall within the standard range of properties for natural material. These values alone do not represent a sufficient basis for any part design and are not intended for use in establishing maximum, minimum, or ranges of values for specification purposes. Colourants or other additives may cause significant variations in data values. Properties of moulded parts can be influenced by a wide variety of factors including, but not limited to, material selection, additives, part design not intended for use in medical or dental implants. Regardless of any such product expressly identified as medical grade (including by MT® product designation or otherwise), Celanese's products are not intended for use in medical or dental implants. Regardless of any such product designation, any determination of the suitability of a particular material and part design for any use contemplated by the users and the manner of such use is the sole responsibility of the users, who must assure themselves that the material as subsequently processed meets the needs of their particular product or use. To the best of our knowledge, the information contained in this publication is accurate; however, we do not assume any liability whatsoever for the accuracy and completeness of such information. The information contained in this publication as a promise or guarantee of specific properties of our products. It is the sole responsibility of the users to investigate whether any existing patents are infringed by the use of the materials mentioned in this publication. Moreover, there is a need to reduce human exposure to many materials the lowest that texist. We recommend that persons intending to rely on any recommendation or to use any equipment, processing technique or material mentioned in this publication should satisfy themselves that they can meet all applicable safety and health standards. We strongly recommend that users seek and achere to the m

© 2023 Celanese or its affiliates. All rights reserved. Celanese®, registered C-ball design and all other trademarks identified herein with ®, TM, SM, unless otherwise noted, are trademarks of Celanese or its affiliates. Fortron is a registered trademark of Fortron Industries LLC. KEPITAL is a registered trademark of Korea Engineering Plastics Company, Ltd.