

# KEPITAL® NX-20 LOF

A emission optimized, friction and wear-resistance grade for general injection molding  
 A friction and wear resistance grade for general injection molding. Emission optimized.

## Rheological properties

Moulding shrinkage, parallel	2.0 %	ISO 294-4, 2577
------------------------------	-------	-----------------

## Typical mechanical properties

Yield stress, 50mm/min	55 MPa	ISO 527-1/-2
Nominal strain at break	18 %	ISO 527-1/-2
Flexural Modulus	2350 MPa	ISO 178
Flexural Strength	76 MPa	ISO 178
Charpy notched impact strength, 23°C	3.4 kJ/m <sup>2</sup>	ISO 179/1eA

## Thermal properties

Melting temperature, 10°C/min	165 °C	ISO 11357-1/-3
Temp. of deflection under load, 1.8 MPa	90 °C	ISO 75-1/-2

## Electrical properties

Volume resistivity	>1E12 Ohm.m	IEC 62631-3-1
Surface resistivity	>1E16 Ohm	IEC 62631-3-2

## Other properties

Density	1380 kg/m <sup>3</sup>	ISO 1183
---------	------------------------	----------