

KEPITAL[®] TE-24 (FU2020) LOF

POM, toughened, medium-high viscosity grade, low emission

KEPITAL® TE-24 (FU2020) LOF is a toughened, medium-high viscosity grade for general injection molding. Suitable for applications requiring higher impact resistance and toughness. A low-emission grade featuring improved heat stability.

Product information

Part Marking Code	> POM-HI <	<		ISO 11469
Rheological properties				
Moulding shrinkage, parallel	1.7	7 %		ISO 294-4, 2577
Typical mechanical properties				
Yield stress, 50mm/min	43	B MPa		ISO 527-1/-2
Yield strain, 50mm/min	1 ⁻	l %		ISO 527-1/-2
Nominal strain at break	50) %		ISO 527-1/-2
Flexural Modulus) MPa		ISO 178
Flexural Strength		↓ MPa		ISO 178
Charpy notched impact strength, 23°C	C 15	5 kJ/m²		ISO 179/1eA
Thermal properties				
Melting temperature, 10°C/min	165	5 °C		ISO 11357-1/-3
Temp. of deflection under load, 1.8 MI	Pa 7 ⁻	°C		ISO 75-1/-2
Coeff. of linear therm. expansion, para	allel 130) E-6/K		ISO 11359-1/-2
Electrical properties				
Volume resistivity	1E12	2 Ohm.	m	IEC 62631-3-1
Surface resistivity	1E16	6 Ohm		IEC 62631-3-2
Electric strength	2	l kV/mr	n	IEC 60243-1
Other properties				
Humidity absorption, 2mm	0.24	1 %		Sim. to ISO 62
Density	1350) kg/m³		ISO 1183
Other Approvals				
Other Approvals	OFM		Oppolition	
	OEM		Specification	

OEMSpecificationGMGMW22P-POM-C2P2



KEPITAL[®] TE-24 (FU2020) LOF

Printed: 2023-08-07

Revised: 2023-05-10 Source: Celanese Materials Database

Page: 2 of 2

NOTICE TO USERS: Values shown are based on testing of laboratory test specimens and represent data that fall within the standard range of properties for natural material. These values alone do not represent a sufficient basis for any part design and are not intended for use in establishing maximum, minimum, or ranges of values for specification purposes. Colourants or other additives may cause significant variations in data values. Properties of moulded parts can be influenced by a wide variety of factors including, but not limited to, material selection, additives, part design not intended for use in medical or dental implants. Regardless of any such product expressly identified as medical grade (including by MT® product designation or otherwise), Celanese's products are not intended for use in medical or dental implants. Regardless of any such product designation, any determination of the suitability of a particular material and part design for any use contemplated by the users and the manner of such use is the sole responsibility of the users, who must assure themselves that the material as subsequently processed meets the needs of their particular product or use. To the best of our knowledge, the information contained in this publication is accurate; however, we do not assume any liability whatsoever for the accuracy and completeness of such information. The information contained in this publication as a promise or guarantee of specific properties of our products. It is the sole responsibility of the users to investigate whether any existing patents are infringed by the use of the materials mentioned in this publication. Moreover, there is a need to reduce human exposure to many materials the lowest that texist. We recommend that persons intending to rely on any recommendation or to use any equipment, processing technique or material mentioned in this publication should satisfy themselves that they can meet all applicable safety and health standards. We strongly recommend that users seek and achere to the m

© 2023 Celanese or its affiliates. All rights reserved. Celanese®, registered C-ball design and all other trademarks identified herein with ®, TM, SM, unless otherwise noted, are trademarks of Celanese or its affiliates. Fortron is a registered trademark of Fortron Industries LLC. KEPITAL is a registered trademark of Korea Engineering Plastics Company, Ltd.