

## KEPITAL<sup>®</sup> TE-25 (FU2025)

toughened, medium-high viscosity grade

KEPITAL® TE-25 is a toughened, medium-high viscosity grade for general injection molding. Suitable for applications requiring much higher impact resistance and toughness than TE-24.

Rheological properties		
Moulding shrinkage, parallel	1.6 %	ISO 294-4, 2577
Typical mechanical properties		
Yield stress, 50mm/min	39 MPa	ISO 527-1/-2
Yield strain, 50mm/min	14 %	ISO 527-1/-2
Nominal strain at break	>50 %	ISO 527-1/-2
Flexural Modulus	1250 MPa	ISO 178
Flexural Strength	46 MPa	ISO 178
Charpy notched impact strength, 23°C	21 kJ/m <sup>4</sup>	<sup>2</sup> ISO 179/1eA
Poisson's ratio	0.355	
Thermal properties		
Melting temperature, 10°C/min	165 °C	ISO 11357-1/-3
Temp. of deflection under load, 1.8 MPa	65 °C	ISO 75-1/-2
Coeff. of linear therm. expansion, parallel	130 E-6/k	ISO 11359-1/-2
Electrical properties		
Volume resistivity	>1E14 Ohm.	m IEC 62631-3-1
Surface resistivity	>1E16 Ohm	IEC 62631-3-2
Electric strength	21 kV/m	m IEC 60243-1
Other properties		
Density	1340 kg/m <sup>2</sup>	<sup>3</sup> ISO 1183
Denoty	To To To Tg/III	

Printed: 2023-08-07

Page: 1 of 1

Revised: 2023-05-10 Source: Celanese Materials Database

NOTICE TO USERS: Values shown are based on testing of laboratory test specimens and represent data that fall within the standard range of properties for natural material. These values alone do not represent a sufficient basis for any part design and are not intended for use in establishing maximum, minimum, or ranges of values for specification purposes. Colourants or other additives may, processing conditions and environmental exposure. Other than those products expressly identified as medical grade (including by MT® product designation or otherwise), Celanese's products are not intended for use in medical or dental implants. Regardless of any such product designation, any determination of the suitability of a particular material and part design for any use contemplated by the users and the manner of such use is the sole responsibility of the users, who must assure themselves that the material as subsequently processed meets the needs of their particular product or use. To the best of our knowledge, the information contained in this publication is accurate; however, we do not assume any liability whatsoever for the accuracy and completeness of such information. The information contained in this publication as a promise or guarantee of specific properties of our groucts. It is the sole responsibility of the users to investigate whether any existing patents are infringed by the use of the materials mentioned in this publication. Moreover, there is a need to reduce human exposure to many materials to he lowest practical limits in view of possible adverse effects. To the extent that any hazards may have been mentioned in this publication, we neither suggest nor guarantee that such hazards are the only ones that exist. We recommend that persons intending to rely on any recommendation or to use any equipment, processing technique or material inductions for handling each material they use, and entrust the handling of such material to adequately trained personnel only. Please call the telephone numbers listed for addi

© 2023 Celanese or its affiliates. All rights reserved. Celanese®, registered C-ball design and all other trademarks identified herein with ®, TM, SM, unless otherwise noted, are trademarks of Celanese or its affiliates. Fortron is a registered trademark of Fortron Industries LLC. KEPITAL is a registered trademark of Korea Engineering Plastics Company, Ltd.