

SANTOPRENE® 201-55W255

A soft, colorable thermoplastic vulcanizate (TPV) in the thermoplastic elastomer (TPE) family. This material is designed for use in residential washing machine and dishwasher applications and contains a stabilization system for protection against copper and other metal-catalyzed degradation. This grade of Santoprene™ TPV is shear-dependent and can be processed on conventional thermoplastics equipment for injection molding or extrusion. It is polyolefin based and recyclable within the manufacturing stream.

Key Features

- Property retention in presence of typical dishwasher and washing machine detergents

Typical mechanical properties

Stress at 100% elongation	1.9 MPa	ISO 527-1/-2 or ISO 37
Stress at break	5.1 MPa	ISO 527-1/-2 or ISO 37
Elongation at break	450 %	ISO 527-1/-2 or ISO 37
Shore A hardness, 15s	60	ISO 48-4 / ISO 868
Compression set at 23 °C, 24h	16 %	ISO 815
Compression set at 70 °C, 24h	35 %	ISO 815
Compression set at 100 °C, 24h	42 %	ISO 815

Other properties

Density	960 kg/m ³	ISO 1183
---------	-----------------------	----------

Processing Texts

Processing Notes	Desiccant drying for 3 hours at 80 °C (180 °F) is recommended. Santoprene™ TPV has a wide temperature processing window from 175 to 230 °C (350 to 450 °F) and is incompatible with acetal and PVC.
------------------	---