

SANTOPRENE® 251-85W232

A hard, colorable, flame retardant thermoplastic vulcanizate (TPV) in the thermoplastic elastomer (TPE) family. This material has good fluid resistance and contains non-ether brominated flame retardants. It does not contain metal deactivators. This grade of Santoprene® TPV is shear-dependent and can be processed on conventional thermoplastics equipment for injection molding, extrusion, blow molding, thermoforming or vacuum forming. It is polyolefin based and recyclable within the manufacturing stream.

Key Features

- UL listed: file #QMFZ2.E80017, Plastics - Component; file #QMFZ8.E80017, Plastics Certified For Canada - Component; file #QMTT2.E86313, Polymeric Materials for Use in Wire, Cable and Flexible Lighting Products - Component.
- Recommended for applications requiring a flame retardant material - UL 94 Vertical Flame rated.
- Recommended for applications requiring excellent flex fatigue resistance.
- Recommended for applications requiring excellent ozone resistance.

Typical mechanical properties

Stress at 100% elongation	4.5 MPa	ISO 527-1/-2 or ISO 37
Stress at break	10.6 MPa	ISO 527-1/-2 or ISO 37
Elongation at break	540 %	ISO 527-1/-2 or ISO 37
Shore A hardness, 15s	89	ISO 48-4 / ISO 868

Flammability

Burning Behav. at thickness h	V-2 class	UL 94
Thickness tested	0.75 mm	UL 94
UL recognition	yes	UL 94

Other properties

Density	1150 kg/m ³	ISO 1183
---------	------------------------	----------

Processing Texts

Processing Notes	Desiccant drying for 3 hours at 80°C (180°F) is recommended. Santoprene® TPV has a wide temperature processing window from 175 to 230°C (350 to 450°F) and is incompatible with acetal and PVC.
------------------	--