



The Polyolefin Company (Singapore) Pte. Ltd.

Office : 150 Beach Road, #10-00 Gateway West, Singapore 189720

Tel: (65) 6292 9622 Fax: (65) 6293 8890, (65) 6292 6595, (65) 6293 2748

Plant : 401 Ayer Merbau Road, Singapore 628285

Website: www.tpc.com.sg

Co. Reg. No.: 198001666D

COSMOTHENE[®] G810-S

CHARACTERISTICS

COSMOTHENE G810-S has excellent cracking resistance, processibility and small pellets

APPLICATIONS

Artificial flower and other injection molding usages.

PHYSICAL PROPERTIES

ITEM	UNIT	G810-S	TEST METHOD
Melt Flow Rate	g/10 mins	35	ASTM D1238
Density	g/cm ³	0.918	ASTM D792
Tensile Strength at break	Mpa	9.8	ASTM D638
Elongation	%	600	ASTM D638
Stiffness	Mpa	160	ASTM D747
Melting Point	°C	105	TPC METHOD

- The figures presented are typical laboratory averages, only for reference.
- The information is based on our current knowledge, is subjected to continuous updates and is intended to suggest/ recommend product applications and to provide typical data on the related properties. It should not therefore be construed as guaranteeing any specific property of the product. TPC makes no warranty of any kind, expressed or implied, regarding the accuracy of these data.



Jan 2011

COSMOPLENE[®]

POLYPROPYLENE

COSMOTHENE[®]

LOW DENSITY POLYETHYLENE

COSMOTHENE[®] EVA

ETHYLENE VINYL
ACETATE COPOLYMER