

VICTREX™ PEEK POLYMERS 450CA40

General Information

Product Description

High performance thermoplastic material, 40% carbon fibre reinforced PolyEtherEtherKetone (PEEK), semi crystalline, granules for injection moulding and extrusion, low flow, FDA food contact compliant, colour black.

Applications for higher strength and stiffness in a static or dynamic system. Excellent wear resistance, low coefficient of friction, low coefficient of thermal expansion. Chemically resistant to aggressive environments.

Material Properties

Physical	Nominal Value	Unit	Test Method
Density (Crystalline)	1.44	g/cm ³	ISO 1183
Spiral Flow ¹	6.50	cm	Internal Method
Molding Shrinkage ²			ISO 294-4
Across Flow	0.50	%	
Flow	0.10	%	
Water Absorption (Saturation, 23°C)	0.25	%	ISO 62
Water Absorption - Saturation (100°C)	0.45	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus (23°C)	35000	MPa	ISO 527-1
Tensile Stress			ISO 527-2
Break, 23°C	285	MPa	
Break, 125°C	175	MPa	
Break, 175°C	105	MPa	
Break, 275°C	65.0	MPa	
Tensile Strain (Break, 23°C)	1.5	%	ISO 527-2
Flexural Modulus (23°C)	30000	MPa	ISO 178
Flexural Stress			ISO 178
23°C	425	MPa	
125°C	290	MPa	
175°C	160	MPa	
275°C	90.0	MPa	
Compressive Stress			ISO 604
23°C	360	MPa	
120°C	230	MPa	
200°C	90.0	MPa	
250°C	60.0	MPa	
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact Strength (23°C)	11	kJ/m ²	ISO 180/A
Unnotched Izod Impact Strength (23°C)	20	kJ/m ²	ISO 180
Hardness	Nominal Value	Unit	Test Method
Shore Hardness (Shore D, 23°C)	88		ISO 868

VICTREX™ PEEK POLYMERS 450CA40

Thermal	Nominal Value	Unit	Test Method
Glass Transition Temperature			ISO 11357-2
Onset	143	°C	
Midpoint	150	°C	
Melting Temperature	343	°C	ISO 11357-3
CLTE			ISO 11359-2
Flow : < 143°C	5.0E-6	cm/cm/°C	
Flow : > 143°C	8.0E-6	cm/cm/°C	
Transverse : < 143°C	3.5E-5	cm/cm/°C	
Transverse : > 143°C	9.0E-5	cm/cm/°C	
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity ³ (23°C)	1.0E+5	ohms·cm	ASTM D4496
Flammability	Nominal Value	Unit	Test Method
Glow Wire Flammability Index (2.0 mm)	960	°C	IEC 60695-2-12
Fill Analysis	Nominal Value	Unit	Test Method
Melt Viscosity (400°C)	850	Pa·s	ISO 11443

Processing Information

Injection	Nominal Value	Unit
Drying Temperature	120 to 150	°C
Drying Time	3.0 to 5.0	hr
Hopper Temperature	< 100	°C
Rear Temperature	380	°C
Middle Temperature	390 to 395	°C
Front Temperature	400	°C
Nozzle Temperature	405	°C
Mold Temperature	190 to 210	°C

Injection Notes

Runner: Die / nozzle >3mm, manifold >3.5mm
Gate: >2mm or 0.5 x part thickness

Notes

¹ Mold Temperature: 200°C, Melt Temperature: 405°C, 1.00 mm

² 405°C nozzle, 200°C tool

³ 1V

Revision Date: 7/17/2023

This information is provided "as is". It is not intended to amount to advice. Use of the product is at the customer's/user's risk. It is the customer's/user's responsibility to thoroughly test the product in each specific application to determine its performance, efficacy and safety for each end-use product, device or other application and compliance with applicable laws, regulations and standards. Mention of a product is no guarantee of availability. Victrex reserves the right to modify products, data sheets, specifications and packaging. **Victrex makes no warranties, express or implied (including, without limitation, any warranty of fitness for a particular purpose or of intellectual property non-infringement) and will not be liable for any loss or damage of any nature (however arising) in connection with customer's/user's use or reliance on this information, except for any liability which cannot be excluded or limited by law.** This document may be modified or retracted at any time without notice to the customer/user.

Victrex Manufacturing Limited (or another member of the Victrex group) is the owner or the licensee of all intellectual property rights in and to this document including the following trademarks, VICTREX, INVIBIO, JUVORA, APTIV, 450G, PEEK-OPTIMA, SHAPING FUTURE PERFORMANCE, LMPAEK, TRIANGLE (Device). All rights are protected by intellectual property rights including copyright under relevant national and international intellectual property laws and treaties. All rights reserved. Copyright © Victrex Manufacturing Limited 2023.