

Technical Data Sheet

Metocene MF650X

Metallocene PP Homopolymer



Product Description

Metocene MF650X is an extremely high melt flow rate homopolymer resin with very narrow molecular weight distribution. It is suitable for melt blown fibers as well as compounding extrusion applications. This material is available as a free-flowing, low dust granule (flake) resin. This product contains no peroxide or peroxide decomposition by-products. It is a low gas fading product.

The very narrow molecular weight distribution and high degree of resin consistency promote finer fibers, enhanced fiber filament thread line continuity as well as reduced fly and lint in melt blown spinning processes. Its extremely high melt flow rate allows reduced processing temperatures and energy savings. This is a low smoke, clean running resin with good thermal and processing stability.

Regulatory Status

For regulatory compliance information, see *Metocene* MF650X [Product Stewardship Bulletin \(PSB\) and Safety Data Sheet \(SDS\)](#).

Status	Commercial: Active
Availability	Asia-Pacific; Europe; North America
Application	Absorption & Filtration; Colour Concentrates; Nonwovens; Wipes/Tissues
Market	Compounding; Textile
Processing Method	Compounding; Melt Blown
Attribute	Extremely High Flow; High Purity; Low Smoke Emission; Narrow Molecular Weight Distribution

Typical Properties	Nominal Value	Units	Test Method
Physical			
Melt Flow Rate, (230 °C/2.16 kg)	1200	g/10 min	ISO 1133-1

Notes

These are typical property values not to be construed as specification limits.

Processing Techniques

Specific recommendations for resin type and processing conditions can only be made when the end use, required properties and fabrication equipment are known.

Company Information

For further information regarding the LyondellBasell company, please visit <http://www.lyb.com/>.

© LyondellBasell Industries Holdings, B.V. 2018

Disclaimer

Information in this document is accurate to the best of our knowledge at the date of publication. The document is designed to provide users general information for safe handling, use, processing, storage, transportation, disposal and release and does not constitute any warranty or quality specification, either express or implied, including any warranty of merchantability or fitness for any particular purpose. Users shall determine whether the product is suitable for their use and can be used safely and legally.

In addition to any prohibitions of use specifically noted in this document, LyondellBasell may further prohibit or restrict the sale of its products into certain applications. For further information, please contact a LyondellBasell representative.

Trademarks

The Trademark referenced within the product name is owned or used by the LyondellBasell family of companies.