

Technical Data Sheet

Clyrell RC124H



Polypropylene, Specialty Products

Product Description

Clyrell RC124H is a high modified polypropylene random copolymer designed for extrusion applications. *Clyrell* RC124H exhibits enhanced optical properties. The main applications of *Clyrell* RC124H are blown film extrusion, sheet extrusion and thermoforming.

Regulatory Status

For regulatory compliance information, see *Clyrell* RC124H [Product Stewardship Bulletin \(PSB\)](#) and [Safety Data Sheet \(SDS\)](#).

Status	Commercial: Active
Availability	Africa-Middle East; Europe
Application	Bags & Pouches; Food Packaging Film; Stationery Film; Textile Packaging Film
Market	Flexible Packaging
Processing Method	Blown Film; Sheet; Thermoforming
Attribute	Good Optical Properties; High Clarity; High Gloss; Random Copolymer

Typical Properties	Nominal Value	Units	Test Method
Physical			
Melt Flow Rate, (230 °C/2.16 kg)	2.2	g/10 min	ISO 1133-1
Density	0.90	g/cm ³	ISO 1183-1
Mechanical			
Flexural Modulus	750	N/mm ²	ISO 178
Tensile Stress at Break, (23 °C, 50 mm/min)	28.0	N/mm ²	ISO 527-1, -2
Tensile Stress at Yield, (23 °C, 50 mm/min)	25.0	N/mm ²	ISO 527-1, -2
Tensile Strain at Break, (23 °C, 50 mm/min)	500	%	ISO 527-1, -2
Tensile Strain at Yield, (23 °C, 50 mm/min)	15.0	%	ISO 527-1, -2
Impact			
Charpy Impact Strength - Notched			
(23 °C, Type 1, Edgewise, Notch A)	45.0	kJ/m ²	ISO 179-1/1eA
(0 °C, Type 1, Edgewise, Notch A)	8.0	kJ/m ²	ISO 179-1/1eA
Thermal			
Vicat Softening Temperature, (A50)	120	°C	ISO 306
Deflection Temperature Under Load, (0.46 N/mm ²)	65	°C	ISO 75B-1, -2

Notes

These are typical property values not to be construed as specification limits.

Processing Techniques

Specific recommendations for resin type and processing conditions can only be made when the end use, required properties and fabrication equipment are known.

Company Information

For further information regarding the LyondellBasell company, please visit <http://www.lyb.com/>.

© LyondellBasell Industries Holdings, B.V. 2018

Disclaimer

Information in this document is accurate to the best of our knowledge at the date of publication. The document is designed to provide users general information for safe handling, use, processing, storage, transportation, disposal and release and does not constitute any warranty or quality specification, either express or implied, including any warranty of merchantability or fitness for any particular purpose. Users shall determine whether the product is suitable for their use and can be used safely and legally.

In addition to any prohibitions of use specifically noted in this document, LyondellBasell may further prohibit or restrict the sale of its products into certain applications. For further information, please contact a LyondellBasell representative.

Trademarks

The Trademark referenced within the product name is owned or used by the LyondellBasell family of companies.