

Technical Data Sheet

Adstif EA648P



High Crystallinity Polypropylene

Product Description

Adstif EA648P is a high crystalline impact copolymer with outstanding mechanical properties. The product features an easy processability, an excellent combination of stiffness and impact strength and good gloss. Adstif EA648P is a single component solution for high stiffness injection moulding applications that is typically used by customers as replacement of mineral filled polypropylene based compounds. This grade is typically used by customers in a wide range of appliances, such as housings for electrical appliances, furniture and technical components. Adstif EA648P is UL listed under file E31765.

Regulatory Status

For regulatory compliance information, see Adstif EA648P [Product Stewardship Bulletin \(PSB\) and Safety Data Sheet \(SDS\)](#).

This grade is not intended for medical and pharmaceutical applications.

Status	Commercial: Active
Availability	Africa-Middle East; Europe
Application	Caps & Closures; Furniture; Housewares
Market	Consumer Products; Rigid Packaging
Processing Method	Injection Molding
Attribute	Good Processability; High Stiffness; Impact Copolymer; Medium Flow; Medium Impact Resistance

Typical Properties	Nominal Value	Units	Test Method
Physical			
Melt Flow Rate, (230 °C/2.16 kg)	18	g/10 min	ISO 1133-1
Density	0.90	g/cm ³	ISO 1183-1
Mechanical			
Tensile Modulus	1750	MPa	ISO 527-1, -2
Tensile Stress at Yield	32	MPa	ISO 527-1, -2
Tensile Strain at Break	50	%	ISO 527-1, -2
Tensile Strain at Yield	5	%	ISO 527-1, -2
Impact			
Charpy Impact Strength - Notched			
(23 °C, Type 1, Edgewise, Notch A)	6.5	kJ/m ²	ISO 179
(0 °C, Type 1, Edgewise, Notch A)	3.0	kJ/m ²	ISO 179
(-20 °C, Type 1, Edgewise, Notch A)	2.5	kJ/m ²	ISO 179
Thermal			
Vicat Softening Temperature, (A50)	153	°C	ISO 306
Heat Deflection Temperature B, (0.45 MPa, Unannealed)	100	°C	ISO 75B-1, -2
Optical			
Gloss, (60°)	70	%	ASTM D2457

Notes

These are typical property values not to be construed as specification limits.

Processing Techniques

Specific recommendations for resin type and processing conditions can only be made when the end use, required properties and fabrication equipment are known.

Company Information

For further information regarding the LyondellBasell company, please visit <http://www.lyb.com/>.

© LyondellBasell Industries Holdings, B.V. 2018

Disclaimer

Information in this document is accurate to the best of our knowledge at the date of publication. The document is designed to provide users general information for safe handling, use, processing, storage, transportation, disposal and release and does not constitute any warranty or quality specification, either express or implied, including any warranty of merchantability or fitness for any particular purpose. Users shall determine whether the product is suitable for their use and can be used safely and legally.

In addition to any prohibitions of use specifically noted in this document, LyondellBasell may further prohibit or restrict the sale of its products into certain applications. For further information, please contact a LyondellBasell representative.

Trademarks

The Trademark referenced within the product name is owned or used by the LyondellBasell family of companies.