

## Technical Data Sheet

### *Adstif*HA612M

High Crystallinity Polypropylene



#### Product Description

*Adstif*HA612M is a high crystallinity medium fluidity polypropylene homopolymer. It does not contain slip or anti-blocking additives and it does not contain Calcium Stearate.

*Adstif*HA612M is typically used by customers for cast film applications where high rigidity and high temperature resistance are required. *Adstif*HA612M is used by customers for the production of coextruded twist wrapping, labels, lamination, metallize able film and textile packaging.

Films produced with *Adstif*HA612M have been reported by customers to exhibits very high stiffness..

#### Regulatory Status

For regulatory compliance information, see *Adstif*HA612M [Product Stewardship Bulletin \(PSB\) and Safety Data Sheet \(SDS\)](#).

<b>Status</b>	Commercial: Active
<b>Availability</b>	Africa-Middle East; Europe
<b>Application</b>	Food Packaging Film; Stationery Film; Twist Wrap Film
<b>Market</b>	Flexible Packaging
<b>Processing Method</b>	Cast Film; Double Bubble
<b>Attribute</b>	Broad Molecular Weight Distribution; Crystalline; High Rigidity; Homopolymer

Typical Properties	Nominal Value	Units	Test Method
<b>Physical</b>			
Melt Flow Rate, (230 °C/2.16 kg)	7.0	g/10 min	ISO 1133-1
Density	0.90	g/cm <sup>3</sup>	ISO 1183-1
<b>Mechanical</b>			
Flexural Modulus	1900	MPa	ISO 178
Tensile Stress at Break	23	MPa	ISO 527-1, -2
Tensile Stress at Yield	37	MPa	ISO 527-1, -2
Tensile Strain at Break	100	%	ISO 527-1, -2
Tensile Strain at Yield	8	%	ISO 527-1, -2
<b>Thermal</b>			
Vicat Softening Temperature, (A/50)	160	°C	ISO 306
Heat Deflection Temperature B, (0.45 MPa, Unannealed)	110	°C	ISO 75B-1, -2

## Notes

These are typical property values not to be construed as specification limits.

## Processing Techniques

Users should determine the conditions necessary to obtain optimum product properties and suitability of the product for the intended application.

## Company Information

For further information regarding the LyondellBasell company, please visit <http://www.lyb.com/>.

© LyondellBasell Industries Holdings, B.V. 2018

## Disclaimer

Information in this document is accurate to the best of our knowledge at the date of publication. The document is designed to provide users general information for safe handling, use, processing, storage, transportation, disposal and release and does not constitute any warranty or quality specification, either express or implied, including any warranty of merchantability or fitness for any particular purpose. Users shall determine whether the product is suitable for their use and can be used safely and legally.

In addition to any prohibitions of use specifically noted in this document, LyondellBasell may further prohibit or restrict the sale of its products into certain applications. For further information, please contact a LyondellBasell representative.

## Trademarks

The Trademark referenced within the product name is owned or used by the LyondellBasell family of companies.