

## Technical Data Sheet

# Clyrell RC213M

Polypropylene, Random Copolymer



### Product Description

*Clyrell* RC213M is a high flow and highly modified polypropylene random copolymer. It contains anti-blocking additives. It does not contain Calcium Stearate.

*Clyrell* RC213M is typically used by customers for manufacturing of oriented and un-oriented films. Typical applications reported by customers are lamination, metallized films, textile and packaging of foodstuffs. In addition, customers also reported that it is particularly suitable as a skin of multilayer twist film.

Customers have been reporting that films produced using *Clyrell* RC213M offer a good balance of properties such as high clarity, brightness, stiffness and medium seal initiation temperature (SIT).

### Regulatory Status

For regulatory compliance information, see *Clyrell* RC213M [Product Stewardship Bulletin \(PSB\) and Safety Data Sheet \(SDS\)](#).

<b>Availability</b>	Africa-Middle East; Asia-Pacific; Europe
<b>Application</b>	Barrier Film; Food Packaging Film; Specialty Film; Textile Packaging Film; Twist Wrap Film
<b>Processing Method</b>	BOPP; Cast Film
<b>Attribute</b>	Good Processability; High Gloss; Random Copolymer; Unspecified Antiblocking

Typical Properties	Nominal Value	Units	Test Method
<b>Physical</b>			
Melt Flow Rate			
(230 °C/2.16 kg)	10.5	g/10 min	ASTM D1238
(230 °C/2.16 kg)	10.5	g/10 min	ISO 1133-1
Density	0.90	g/cm <sup>3</sup>	ASTM D792
<b>Mechanical</b>			
Flexural Modulus	1000	MPa	ISO 178
Tensile Stress at Break	30	MPa	ISO 527-1, -2
Tensile Stress at Yield	27	MPa	ISO 527-1, -2
Tensile Strain at Break	600	%	ISO 527-1, -2
Tensile Strain at Yield	11	%	ISO 527-1, -2
<b>Impact</b>			
Charpy Impact Strength - Notched			
(23 °C)	6	kJ/m <sup>2</sup>	ISO 179-1/1eA
(0 °C)	2	kJ/m <sup>2</sup>	ISO 179
<b>Thermal</b>			
Vicat Softening Temperature, (A/50)	130	°C	ISO 306
Heat Deflection Temperature B, (0.45 MPa, Unannealed)	68	°C	ISO 75B-1, -2
<b>Optical</b>			
Haze, (50 µm)	<1	%	ASTM D1003

**Notes**

These are typical property values not to be construed as specification limits.

**Processing Techniques**

Specific recommendations for resin type and processing conditions can only be made when the end use, required properties and fabrication equipment are known.

**Company Information**

For further information regarding the LyondellBasell company, please visit <http://www.lyb.com/>.

© LyondellBasell Industries Holdings, B.V. 2018

**Disclaimer**

Information in this document is accurate to the best of our knowledge at the date of publication. The document is designed to provide users general information for safe handling, use, processing, storage, transportation, disposal and release and does not constitute any warranty or quality specification, either express or implied, including any warranty of merchantability or fitness for any particular purpose. Users shall determine whether the product is suitable for their use and can be used safely and legally.

In addition to any prohibitions of use specifically noted in this document, LyondellBasell may further prohibit or restrict the sale of its products into certain applications. For further information, please contact a LyondellBasell representative.

**Trademarks**

The Trademark referenced within the product name is owned or used by the LyondellBasell family of companies.