Technical Data Sheet

Hostalen PP H5416K



Polypropylene, Random Copolymer

Product Description

Hostalen PP H5416K is a nucleated polypropylene rando copolymer with high melt viscosity for extrusion, and high heat and extraction stability. Typical customer applications are industrial pipe, heating and cooling plumbing.

Regulatory Status

For regulatory compliance information, see *Hostalen PP H5416K Product Stewardship Bulletin (PSB) and Safety Data Sheet (SDS).*

Status Commercial: Active

Availability Africa-Middle East; Asia-Pacific; Australia and New Zealand

Application Industrial; Plumbing, Heating & Cooling

Market Industrial, Building & Construction; Pipe

Processing Method Pipe; Sheet

Attribute Antioxidant; Random Copolymer

| | Nominal | | |
|---|---------|----------|-------------|
| Typical Properties | Value | Units | Test Method |
| Physical | | | |
| Melt Flow Rate, (230 °C/2.16 kg) | 0.3 | g/10 min | ASTM D1238 |
| Density | 0.90 | g/cm³ | ASTM D792 |
| Mechanical | | | |
| Flexural Modulus | 850 | MPa | ASTM D790 |
| Tensile Strength at Yield | 27 | MPa | ASTM D638 |
| Tensile Elongation at Yield | 10 | % | ASTM D638 |
| Impact | | | |
| Notched Izod Impact Strength, (23 °C) | 230 | J/m | ASTM D256 |
| Thermal | | | |
| Vicat Softening Point | 123 | °C | ASTM D1525 |
| Deflection Temperature Under Load, (0.46 N/mm²) | 83 | °C | ASTM D648 |
| | | | |

Manainal

LyondellBasell Technical Data Sheet Date: 12/3/2023

Notes

These are typical property values not to be construed as specification limits.

Company Information

For further information regarding the LyondellBasell company, please visit http://www.lyb.com/.

© LyondellBasell Industries Holdings, B.V. 2018

Disclaimer

Information in this document is accurate to the best of our knowledge at the date of publication. The document is designed to provide users general information for safe handling, use, processing, storage, transportation, disposal and release and does not constitute any warranty or quality specification, either express or implied, including any warranty of merchantability or fitness for any particular purpose. Users shall determine whether the product is suitable for their use and can be used safely and legally.

In addition to any prohibitions of use specifically noted in this document, LyondellBasell may further prohibit or restrict the sale of its products into certain applications. For further information, please contact a LyondellBasell representative.

Trademarks

The Trademark referenced within the product name is owned or used by the LyondellBasell family of companies.

LyondellBasell Technical Data Sheet Date: 12/3/2023 Hostalen PP H5416K Recipient Tracking #: Request #: 4725287