# **Technical Data Sheet**

# Moplen RP242G



Polypropylene, Random Copolymer

## **Product Description**

Low Melt Flow Polypropylene Random Copolymer Resin with High Clarity.

#### **Regulatory Status**

For regulatory compliance information, see *Moplen* RP242G <u>Product Stewardship Bulletin (PSB) and Safety</u> <u>Data Sheet (SDS)</u>.

Status	Commercial: Active	
Availability	Africa-Middle East; Asia-Pacific; Australia and New Zealand	
Application	Bottles For Consumer Goods; Bottles for Industrial Use; Stationery Film	
Market	Industrial Packaging; Rigid Packaging	
Processing Method	Extrusion Blow Molding; Sheet; Thermoforming	
Attribute	Good Impact Resistance; High Clarity; Nucleated; Random Copolymer	

	Nominal		
Typical Properties	Value	Units	Test Method
Physical			
Melt Flow Rate, (230 °C/2.16 kg)	1.5	g/10 min	ASTM D1238
Density	0.90	g/cm³	ASTM D792
Mechanical			
Flexural Modulus	920	MPa	ASTM D790
Tensile Strength at Yield	27	MPa	ASTM D638
Tensile Elongation at Yield	15	%	ASTM D638
Impact			
Notched Izod Impact Strength, (23 °C)	No Break		ASTM D256
Thermal			
Deflection Temperature Under Load	82	°C	ASTM D648

## Notes

These are typical property values not to be construed as specification limits.

#### **Company Information**

For further information regarding the LyondellBasell company, please visit http://www.lyb.com/.

© LyondellBasell Industries Holdings, B.V. 2018

#### Disclaimer

Information in this document is accurate to the best of our knowledge at the date of publication. The document is designed to provide users general information for safe handling, use, processing, storage, transportation, disposal and release and does not constitute any warranty or quality specification, either express or implied, including any warranty of merchantability or fitness for any particular purpose. Users shall determine whether the product is suitable for their use and can be used safely and legally.

In addition to any prohibitions of use specifically noted in this document, LyondellBasell may further prohibit or restrict the sale of its products into certain applications. For further information, please contact a LyondellBasell representative.

#### Trademarks

The Trademark referenced within the product name is owned or used by the LyondellBasell family of companies.