

## Technical Data Sheet / 技術資料表

## 2022/05/05

Globalene PT181	Polypropylene Ho	mopolymer }	聚丙烯單聚合物
Features 特性:	Typical Application 一般應用:		
· Good thermoformability 熱成型性佳	• Extrusion: thick sheet, pipe 厚板、管材		
・Good stiffness 剛性佳	• Thermoforming: tray, bowl, jelly cup 碗盤、果凍杯		
Typical Property 一般性質	Test Method 測試方法	Unit 單位	Value 數值
Melt flow rate (230℃, 2.16kg) 熔融流率	ASTM D1238	g/10min	0.45
Density 密度	ASTM D792	g/cm <sup>3</sup>	0.902
Elongation at yield 降伏點伸張率	ASTM D638	%	11
Elongation at break 斷裂點伸張率	ASTM D638	%	468
Tensile strength at yield 降伏點抗張強度	ASTM D638	kg/cm <sup>2</sup>	350
Flexural modulus 彎曲彈性係數	ASTM D790	kg/cm <sup>2</sup>	14700
Rockwell hardness 洛氏硬度	ASTM D785	R scale	95
Heat deflection temperature (4.6 kg/cm²) 熱變形溫度	ASTM D648	°C	95
Izod impact strength, notched 23℃ 艾氏衝擊強度, 切口 23℃	ASTM D256	kg-cm/cm	6.6
Mold shrinkage 收縮率	ASTM D955	%	1.5

## Storage and Handling 儲放與處置

The inspected and qualified PP pellets will have a shelf life of minimum two years which is estimated from production date, if it is stored at LCY's best condition of proper temperature below 40°C, adequate humidity below 80%, complete package and indoor warehouse with specific protection from damage. However customers might not fully follow the recommendation to conduct the optimal storage condition, the shelf life is recommended six months only at customer site as received.

本公司所生產聚丙烯(塑膠粒)經首次產品驗證程序確認品質後,在適合的溫度(低於 40°C)、適當的濕度(低於 80%)、包裝袋完整、且具有防護設備的倉庫儲存下,其有效使用期限至少 2 年(以製造日期起算)。考量客戶端的儲存條件可能無法完全依照本公司建議來執行,客戶在購入聚丙烯產品(塑膠粒)後,保存期限建議最高為 6 個月。

## Disclaimer 免責聲明

- The values quoted here are typical of the grade. It should not be construed as specification. 這裡引用的是該牌號的典型值。它不應該被解釋為產品規格/規範。
- Ultimately customers must make their own independent determination that these products are suitable for the intended use, and their use of our product is safe, lawful (except as provided in the above information) and technically suitable in their intended applications.

客戶必須根據其預期或打算的最終成品用途,來判斷與決定列於此的產品(材料)是適合的,並且考慮到這樣的材料與用途組合不僅 能符合相關安全與法規要求(除了以上提供的資料外),並且也滿足在技術層面的需求。

> 3F, No. 85, Bade Road, Sec. 4, Taipei 105, Taiwan Tel: +886 2 2763 1611 Fax: +886 2 2764 5749