

# **TEST REPORT**

APPLICANT : HYOSUNG CHEMICAL CORPORATION

ADDRESS: 235, Banpo-daero, Seocho-gu,

Seoul, Korea

PAGE: 1 of 5

REPORT NO. RT19R-S4334-012-E

DATE: Oct. 02, 2019

SAMPLE DESCRIPTION : The following submitted sample(s) said to be:-

NAME/TYPE OF PRODUCT : Topilene® R601

NAME OF MATERIAL : Polypropylene

SAMPLE ID NO. : RT19R-S4334-012

MANUFACTURER/VENDOR : HYOSUNG CHEMICAL CORPORATION

SAMPLE RECEIVED : Sep. 24, 2019

TESTING DATE : Sep. 24, 2019 ~ Oct. 02, 2019

TEST METHOD(S) : Please see the following page(s).
TEST RESULT(S) : Please see the following page(s).

Approved by,

Authorized by,

Authenticity check

Jade Jang / Lab. Technical Manager

Bo Park / Lab. General Manager



 $<sup>{}^{*}</sup>$  Note 1 : The test results presented in this report refer only to the object tested.

<sup>\*</sup> Note 2 : This report shall not be reproduced except in full without the written approval of the testing laboratory.

<sup>\*</sup> Note 3 : This report is not related to the scope of Korea laboratory accreditation scheme.



# **TEST REPORT**

PAGE: 2 of 5

DATE: Oct. 02, 2019

REPORT NO. RT19R-S4334-012-E

SAMPLE ID NO. : RT19R-S4334-012 SAMPLE DESCRIPTION : Topilene® R601

TEST ITEM	UNIT	TEST METHOD	MDL	RESULT
Cadmium (Cd)	mg/kg	With reference to IEC 62321-5 Edition 1.0 : 2013,	0.5	N.D.
Lead (Pb)	mg/kg	by acid digestion and determined by ICP-OES	5	N.D.
Mercury (Hg)	mg/kg	With reference to IEC 62321-4 Edition 1.0 : 2013, by acid digestion and determined by ICP-OES	2	N.D.
Hexavalent Chromium (Cr <sup>6+</sup> )	mg/kg	With reference to IEC 62321-7-2 Edition 1.0 : 2017, by alkaline/toluene digestion and determined by UV-VIS Spectrophotometer	8	N.D.
Polybrominated Biphenyl (PBBs)				
Monobromobiphenyl	mg/kg		5	N.D.
Dibromobiphenyl	mg/kg		5	N.D.
Tribromobiphenyl	mg/kg		5	N.D.
Tetrabromobiphenyl	mg/kg	With reference to	5	N.D.
Pentabromobiphenyl	mg/kg	IEC 62321-6 Edition 1.0 : 2015,	5	N.D.
Hexabromobiphenyl	mg/kg	by solvent extraction and	5	N.D.
Heptabromobiphenyl	mg/kg	determined by GC/MS	5	N.D.
Octabromobiphenyl	mg/kg		5	N.D.
Nonabromobiphenyl	mg/kg		5	N.D.
Decabromobiphenyl	mg/kg		5	N.D.
Polybrominated Diphenyl Ether (F				
Monobromodiphenyl ether	mg/kg		5	N.D.
Dibromodiphenyl ether	mg/kg		5	N.D.
Tribromodiphenyl ether	mg/kg		5	N.D.
Tetrabromodiphenyl ether	mg/kg	With reference to	5	N.D.
Pentabromodiphenyl ether	mg/kg	IEC 62321-6 Edition 1.0 : 2015,	5	N.D.
Hexabromodiphenyl ether	mg/kg	by solvent extraction and	5	N.D.
Heptabromodiphenyl ether	mg/kg	determined by GC/MS	5	N.D.
Octabromodiphenyl ether	mg/kg		5	N.D.
Nonabromodiphenyl ether	mg/kg		5	N.D.
Decabromodiphenyl ether	mg/kg		5	N.D.

Tested by: Jooyeon Lee, Seulgi Park, Miseon Lee

Notes: mg/kg = ppm = parts per million

< = Less than

N.D. = Not detected ( <MDL ) MDL = Method detection limit



Seoul Office: Tel: 02-6090-9550 Fax: 02-3409-0025 Web Site: intertek.co.kr
Seoul Lab. Address: 7, Achasan-ro 5-gil, Seongdong-gu, Seoul, 04793 Korea
Ulsan Lab. Address: 34, Yongam-gil, Chongryang-myeon, Ulju-gun, Ulsan 44989 Korea





SAMPLE ID NO.

# **TEST REPORT**

PAGE: 3 of 5

DATE: Oct. 02, 2019

REPORT NO. RT19R-S4334-012-E

: RT19R-S4334-012

SAMPLE DESCRIPTION: Topilene® R601

TEST ITEM	CAS NO.	UNIT	TEST METHOD	MDL	RESULT
Dibutyl phthalate (DBP)	84-74-2	mg/kg	With reference to IEC 62321-8 Edition 1.0 : 2017,	50	N.D.
Di(2-ethylhexyl) phthalate (DEHP)	117-81-7	mg/kg		50	N.D.
Benzyl butyl phthalate (BBP)	85-68-7	mg/kg	by solvent extraction and determined by GC/MS	50	N.D.
Diisobutyl phthalate (DIBP)	84-69-5	mg/kg		50	N.D.

Tested by: Miseon Lee

Notes: mg/kg = ppm = parts per million

< = Less than

N.D. = Not detected ( <MDL )
MDL = Method detection limit

<sup>\*</sup> View of sample as received;-







SAMPLE ID NO.


# **TEST REPORT**

PAGE: 4 of 5

DATE: Oct. 02, 2019

REPORT NO. RT19R-S4334-012-E

: RT19R-S4334-012



Remarks:
\*1 · List of appropriate acid ·

. List of appropriate acid.	
Material	Acid added for digestion
Polymers	HNO <sub>3</sub> , HCl, HF, H <sub>2</sub> O <sub>2</sub> , H3BO <sub>3</sub>
Metals	HNO₃, HCI, HF
Electronics	HNO <sub>3</sub> , HCl, H <sub>2</sub> O <sub>2</sub> , HBF <sub>4</sub>

\*2 : The samples were dissolved totally by pre-conditioning method according to above flow chart.





# TEST REPORT


PAGE: 5 of 5

DATE: Oct. 02, 2019

REPORT NO. RT19R-S4334-012-E

SAMPLE ID NO. : RT19R-S4334-012 SAMPLE DESCRIPTION : Topilene® R601

Flow Chart (Phthalates)



#### \*\*\*\*\* End of Report \*\*\*\*\*

Except where explicitly agreed in writing, all work and services performed by Intertek is subject to our standard Terms and Conditions which can be obtained at our website: http://www.intertek.com/terms/. Intertek's responsibility and liability are limited to the terms and conditions of the agreement.

This report is made solely on the basis of your instructions and / or information and materials supplied by you and provide no warranty on the tested sample(s) be truly representative of the sample source. The report is not intended to be a recommendation for any particular course of action, you are responsible for acting as you see fit on the basis of the report results. Intertek is under no obligation to refer to or report upon any facts or circumstances which are outside the specific instructions received and accepts no responsibility to any parties whatsoever, following the issue of the report, for any matters arising outside the agreed scope of the works. This report does not discharge or release you from your legal obligations and duties to any other person. You are the only one authorized to permit copying or distribution of this report (and then only in its entirety). Any such third parties to whom this report may be circulated rely on the content of the report solely at their own risk.

This report shall not be reproduced, except in full.

