

ABS樹脂

Formosa Chemical & Fibre Corporation



項目	單位	測試方式	測試條件	一般級
型號				AG15A1-H
熔融指數	g/10 min	ASTM D-1238	220°C × 10kg	21
熔融指數	g/10 min	ASTM D-1238	200°C × 5kg	2.2
IZOD沖擊強度	kg-cm/cm	ASTM D-256	23 °C, 1/4", Notched	24
比重	-	ASTM D-792	23°C/23°C	1.05
抗張強度	kg/cm ²	ASTM D-638	23 °C, 50mm/min	460
彎曲強度	kg/cm ²	ASTM D-790	23 °C, 15mm/min	810
彎曲模數	kg/cm ²	ASTM D-790	23 °C, 15mm/min	26000
洛氏硬度	R-scale	ASTM D-785	23 °C	R-110
韋式軟化點	°C	ASTM D-1525	Annealed, 50N, 50°C/h	94
熱變形溫度	°C	ASTM D-648	Annealed, 1.8Mpa 1/4"厚, 120°C/h	95
熱變形溫度	°C	ASTM D-648	Unannealed, 1.8Mpa 1/4" 厚, 120°C/h	85
燃燒性		UL-94	File No. E162823	HB 1 ~ 3 mm
特性	高光澤性、中耐衝擊性			

All tests were run under laboratory conditions, ASTM, ISO testing procedures.
The data are intended as a general guide only.

Formosa Chemicals & Fibre Corp. Plastics Div.

TEL:+886-2-27122211 FAX: +886-2-27131649
Address: 11470 台北市內湖區南京東路六段380號A2棟



www.fcfc-plastics.com