

SABIC® PP 501P

PP HOMOPOLYMER

DESCRIPTION

SABIC® PP 501P is a multi purpose grade for extrusion applications. Application: SABIC® PP 501P is typically used (by our customers) for extrusion of tapes and strapping.

Health, Safety and Food Contact regulations: Material Safety Data Sheets (MSDS) and Product Safety declarations are available on our Internet site

<http://www.SABIC.com>

IMDS ID: 7172624

TYPICAL PROPERTY VALUES

Revision 20210702

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
POLYMER PROPERTIES			
Melt Flow Rate (MFR)			
at 230 °C and 2.16 kg	0.8	dg/min	ISO 1133
Density	905	kg/m³	ASTM D1505
Molecular Weight Distribution	Broad	-	-
Isotacticity	Medium	-	-
MECHANICAL PROPERTIES			
Tensile test			
stress at yield	37	MPa	ISO 527-2 1A
strain at yield	10	%	ISO 527-2 1A
tensile modulus	1550	MPa	ISO 527-2 1A
THERMAL PROPERTIES			
Vicat Softening Temperature			
at 50 N (VST/B)	88	°C	ISO 306
at 10 N (VST/A)	152	°C	ISO 306

STORAGE AND HANDLING

Avoid prolonged storage in open sunlight, high temperatures (<50 °C) and /or high humidity as this could well speed up alteration and consequently loss of quality of the material and /or its packaging. Keep material completely dry for good processing.

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.